sales@murada.co.id
www.murada.co.id



GRAINGER APPROVED Sheet GaroltXX 24 x24 0.03125 T Brw Opq, 55PG24

Item **28NVR7174** Mfr. Model **BULKCSGXX14**

Product Details

Item Reference: **55PG24**	Width (in): **24**
Brand: **GRAINGER APPROVED**	Height (in): **0.1**
Weight (lb): **0.9**	Harmonization Code: **3920940000**
Length (in): **24**	

Product Description

XX Fiberglass Epoxy Laminate Sheet Material Fiberglass Epoxy Laminate Color Brown Clarity Opaque Overall Length 24 in Tensile Strength 15 000 psi Maximum Temperature 250 Degrees F Minimum Temperature 0 Degrees F Density 0.049 lb/cu in Standards UL 94 HB Impact Strength 0.6 ft-lb/in Hardness Rating Extra Hard Friction Coefficient Not Applicable Corrosion and Chemical Resistance Fair Friction Rating Not Rated Grade XX Hardness Rockwell M110 Impact Strength Rating Poor