



GRAINGER APPROVED PlstcSht GaroltXX 12 x24 0.25 T Brw Opq, 55PG40

Item **28NVR7190** Mfr. Model **BULKCSGXX31**

Product Details

Item Reference: 55PG40	Width (in): 12
Brand: GRAINGER APPROVED	Height (in): 0.3
Weight (lb): 3.53	Harmonization Code: 3920940000
Length (in): 24	Country of Origin: China

Product Description

XX Fiberglass Epoxy Laminate Sheet Material Fiberglass Epoxy Laminate Color Brown Clarity Opaque Overall Length 24 in Tensile Strength 15 000 psi Maximum Temperature 250 Degrees F Minimum Temperature 0 Degrees F Density 0.049 lb/cu in Standards UL 94 HB Impact Strength 0.6 ft-lb/in Hardness Rating Extra Hard Friction Coefficient Not Applicable Corrosion and Chemical Resistance Fair Friction Rating Not Rated Grade XX Hardness Rockwell M110 Impact Strength Rating Poor