sales@murada.co.id
www.murada.co.id



GRAINGER APPROVED PlstcSht GaroliteG11 6 x6 0.5 T Grn Opq, 55RN51

Item **28NVR7442** Mfr. Model **BULKCSGG1159**

Product Details

Item Reference: **55RN51**	Width (in): **5.9**
Brand: **GRAINGER APPROVED**	Height (in): **0.5**
Weight (lb): **1.3**	Harmonization Code: **3920940000**
Length (in): **5.9**	

Product Description

G-11 Fiberglass Epoxy Laminate Sheet Material Fiberglass Epoxy Laminate Color Green Clarity Opaque Overall Length 6 in Tensile Strength 37 000 psi Maximum Temperature 300 Degrees F Minimum Temperature 0 Degrees F Density 0.066 lb/cu in Standards UL 94 HB Impact Strength 12 ft-lb/in Hardness Rating Extra Hard Friction Coefficient Not Applicable Corrosion and Chemical Resistance Good Friction Rating Not Rated Grade G-11 Hardness Rockwell M110 Impact Strength Rating Excellent