sales@murada.co.id
www.murada.co.id



GRAINGER APPROVED PlstcSht GarolitCE 24 x24 0.5 T Brw Opq, 55RJ16

Item **28NVR7530** Mfr. Model **BULKCSGCE20**

Product Details

Item Reference: **55RJ16**	Width (in): **24**
Brand: **GRAINGER APPROVED**	Height (in): **0.5**
Weight (lb): **14.1**	Harmonization Code: **3920940000**
Length (in): **24**	

Product Description

CE Fiberglass Epoxy Laminate Sheet Material Fiberglass Epoxy Laminate Color Brown Clarity Opaque Overall Length 24 in Tensile Strength 10 000 psi Maximum Temperature 250 Degrees F Minimum Temperature 0 Degrees F Density 0.049 lb/cu in Standards UL 94 HB Impact Strength 1.7 ft-lb/in Hardness Rating Hard Friction Coefficient Not Applicable Corrosion and Chemical Resistance Fair Friction Rating Not Rated Grade CE Hardness Rockwell M100 Impact Strength Rating Poor