sales@murada.co.id
www.murada.co.id



GRAINGER APPROVED PlstcSht GaroltCE 24 x24 0.75 T Brw Opq, 55RJ18

Item **28NVR7532** Mfr. Model **BULKCSGCE22**

Product Details

Item Reference: **55RJ18**	Width (in): **24**
Brand: **GRAINGER APPROVED**	Height (in): **0.8**
Weight (lb): **21.17**	Harmonization Code: **3920940000**
Length (in): **24**	

Product Description

CE Fiberglass Epoxy Laminate Sheet Material Fiberglass Epoxy Laminate Color Brown Clarity Opaque Overall Length 24 in Tensile Strength 10 000 psi Maximum Temperature 250 Degrees F Minimum Temperature 0 Degrees F Density 0.049 lb/cu in Standards UL 94 HB Impact Strength 1.7 ft-lb/in Hardness Rating Hard Friction Coefficient Not Applicable Corrosion and Chemical Resistance Fair Friction Rating Not Rated Grade CE Hardness Rockwell M100 Impact Strength Rating Poor