sales@murada.co.id
www.murada.co.id



GRAINGER APPROVED PlstcSht GaroltCE 12 x12 0.75 T Brw Opq, 55RJ44

Item **28NVR7558** Mfr. Model **BULKCSGCE48**

Product Details

Item Reference: **55RJ44**	Width (in): **12**
Brand: **GRAINGER APPROVED**	Height (in): **0.8**
Weight (lb): **5.4**	Harmonization Code: **3920940000**
Length (in): **12**	

Product Description

CE Fiberglass Epoxy Laminate Sheet Material Fiberglass Epoxy Laminate Color Brown Clarity Opaque Overall Length 12 in Tensile Strength 10 000 psi Maximum Temperature 250 Degrees F Minimum Temperature 0 Degrees F Density 0.049 lb/cu in Standards UL 94 HB Impact Strength 1.7 ft-lb/in Hardness Rating Hard Corrosion and Chemical Resistance Fair Friction Rating Not Rated Grade CE Hardness Rockwell M100 Impact Strength Rating Poor Length Tolerance +/-1.000 in Machinability Good