sales@murada.co.id
www.murada.co.id



GRAINGER APPROVED PlstcSht GaroliteCE 6 x6 1.25 T Brw Opq, 55RJ59

Item **28NVR7573** Mfr. Model **BULKCSGCE63**

Product Details

Item Reference: **55RJ59**	Width (in): **6**
Brand: **GRAINGER APPROVED**	Height (in): **1.3**
Weight (lb): **2.21**	Harmonization Code: **3920940000**
Length (in): **6**	

Product Description

CE Fiberglass Epoxy Laminate Sheet Material Fiberglass Epoxy Laminate Color Brown Clarity Opaque Overall Length 6 in Tensile Strength 10 000 psi Maximum Temperature 250 Degrees F Minimum Temperature 0 Degrees F Density 0.049 lb/cu in Standards UL 94 HB Impact Strength 1.7 ft-lb/in Hardness Rating Hard Friction Coefficient Not Applicable Corrosion and Chemical Resistance Fair Friction Rating Not Rated Grade CE Hardness Rockwell M100 Impact Strength Rating Poor