sales@murada.co.id
www.murada.co.id



WESTWARD Mig Welding Wire 0.023in. AWS A5.9, 20AN38

Item **33GXH0789** Mfr. Model **20AN38**

Product Details

Item Reference: **20AN38**	Width (in): **4**
Brand: **WESTWARD**	Height (in): **1.8**
Weight (lb): **2.12**	Harmonization Code: **7223000000**
Length (in): **4**	

Product Description

Mig Welding Wire AWS Classification ER308Si ER308LSi Material Stainless Steel Process MIG Welding (GMAW) Wire Diameter 0.023 in Tensile Strength (As Welded) 85 ksi Yield Strength (Minimum Required) 55 ksi Yield Strength (As Welded) 55 ksi Spool Type Plastic Spool Series ER308LSi Weight 2 lb For Material Type Stainless Steel to Stainless Steel For Material Grade 304L 304LN 308L Welding Current Designation DCEP