sales@murada.co.id
www.murada.co.id



WESTWARD Mig Welding Wire 0.035in. AWS A5.9, 20AN78

Item **33GXH0807** Mfr. Model **20AN78**

Product Details

Item Reference: **20AN78**	Width (in): **12**
Brand: **WESTWARD**	Height (in): **4**
Weight (lb): **30**	Harmonization Code: **7223000000**
Length (in): **12**	

Product Description

Mig Welding Wire AWS Classification ER309Si ER309LSi Material Stainless Steel Process MIG Welding (GMAW) Wire Diameter 0.035 in Tensile Strength (As Welded) 87 ksi Yield Strength (Minimum Required) 64 ksi Yield Strength (As Welded) 64 ksi Spool Type Plastic Spool Series ER309LSi Weight 30 lb For Material Type Stainless Steel to Carbon Steel Stainless Steel to Low-Alloy Steel Stainless Steel to Stainless Steel For Material Grade 304 304N 305 308 309 309S