sales@murada.co.id
www.murada.co.id



WESTWARD Filler Metal 0.035in. AWS A5.28, 20AP71

Item **33GXH0843** Mfr. Model **20AP71**

Product Details

Item Reference: **20AP71**	Width (in): **2**
Brand: **WESTWARD**	Height (in): **3.75**
Weight (lb): **2**	Harmonization Code: **7229909000**
Length (in): **3.75**	

Product Description

Mig Welding Wire AWS Classification ER80S-D2 Material Low-Alloy Steel Process MIG Welding (GMAW) Wire Diameter 0.035 in Tensile Strength (As Welded) 80 ksi Yield Strength (Minimum Required) 68 ksi Yield Strength (As Welded) 68 ksi Spool Type Plastic Spool Series ER80S-D2 Weight 2 lb For Material Type Low-Alloy Steel to Low-Alloy Steel For Material Grade ASTM A182 ASTM A217 ASTM A234 ASTM A335 ASTM A336 Welding Current Designation DCEP