sales@murada.co.id
www.murada.co.id



WESTWARD K4393 Stick Electrode Nickel 99 3/32 in 1lb, 41R182

Item **33GXH1598** Mfr. Model **41R182**

Product Details

Item Reference: **41R182**	Width (in): **1.5**
Brand: **WESTWARD**	Height (in): **1.5**
Weight (lb): **1.14**	Harmonization Code: **7215500015**
Length (in): **15.3**	

Product Description

K4393 Stick Electrode AWS Classification ENi-CI Material Cast Iron Process Stick Welding (SMAW) Overall Diameter 3/32 in Overall Length 14 in Tensile Strength (Minimum Required) 40 ksi Tensile Strength (As Welded) 40 to 65 ksi Yield Strength (Minimum Required) 38 ksi Yield Strength (As Welded) 38 to 60 ksi Series ENi-CI Weight 1 lb For Material Type Cast Iron to Carbon Steel Cast Iron to Cast Iron Cast Iron to Stainless Steel Welding Current Designation DCEP